

MARCH 2016

UGL NUDECK WOOD AND CONCRETE RESTORATIVE COATING TINTING  
FORMULATIONS USING TWO TINT BASES

MATCHING: UGL NUDECK WOOD AND CONCRETE RESTORATIVE  
COATING COLORS

SYSTEM: **DO-IT-BEST GEOSHADES** USING 32 INCREMENTS PER FLUID  
OUNCE

EXPLANATION OF NOTATION: The amount of colorant to be added is listed in two columns under the container size. The first column under OZ. lists the number(s) of full fluid ounces of colorant to add. If a zero appears in this column, no full fluid ounces are added, only fractions of a fluid ounce. The second column under the heading 32nds, lists the number(s) of fractions, 32nds, of a fluid ounce to add. If a zero appears in this column, no fractions are added, only full fluid ounces. If you have any questions on these formulas please contact UGL at 1-800-845-5227 before starting to tint.

IMPORTANT: Due to the differences between the pigment used in the ready-mixed colors and those used in tinting systems, minor variations are possible. For this reason, store-tinted colors should NOT be used to complete a job started with ready-mixed colors or vice versa.

UGL can only control colors of their own manufacture. Therefore, we CANNOT guarantee that the formulas as indicated will be exact matches. Colors as listed represent our matches to color chips. It is advisable to PRE-DETERMINE the formulas, as being used, will provide the proper color match. UGL cannot assume any responsibility for any changes in shade that may occur.

COLORANTS

Black

Blue

Light Yellow

Magenta

New Green

Red Oxide

Umber

White

Yellow Oxide

# UGL NUDECK WOOD AND CONCRETE RESTORATIVE COATING COLORS USING TWO TINT BASES – DO-IT-BEST GEOSHADES

## BEECHWOOD GRAY

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	1	16	Black	5	8
			Red Oxide	0	5	Red Oxide	0	17 ½
			Yellow Oxide	1	26	Yellow Oxide	6	11

## BEIGE

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Red Oxide	0	3 ½	Red Oxide	0	12 ¼
			Umber	2	7	Umber	7	24 ½
			Yellow Oxide	1	2 ½	Yellow Oxide	3	24 ¾

## BLACK CANYON

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	8	0	Black	28	0
			New Green	0	8	New Green	0	28

## BUTTERNUT

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	1	2	Black	3	23
			Light Yellow	4	16	Light Yellow	15	24
			Red Oxide	0	31	Red Oxide	3	12 ½
			White	2	8	White	7	28

## CALIFORNIA RUSTIC

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	0	22	Black	2	13
			Red Oxide	4	0	Red Oxide	14	0
			White	0	16	White	1	24
			Yellow Oxide	5	4	Yellow Oxide	17	30

# UGL NUDECK WOOD AND CONCRETE RESTORATIVE COATING COLORS USING TWO TINT BASES – DO-IT-BEST GEOSHADES

## CAPE COD GRAY

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	0	16	Black	1	24
			Red Oxide	0	½	Red Oxide	0	1 ¾
			Umber	0	21	Umber	2	9 ½

## CEDARWOOD

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Red Oxide	0	17 ½	Red Oxide	1	29 ¼
			Umber	4	10	Umber	15	3
			Yellow Oxide	5	12	Yellow Oxide	18	26

## CHOCOLATE

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Red Oxide	0	12	Red Oxide	1	10
			Umber	8	8	Umber	28	28
			Yellow Oxide	0	18	Yellow Oxide	1	31

## COLONIAL YELLOW

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	0	8	Black	0	28
			Red Oxide	0	2	Red Oxide	0	7
			White	3	16	White	12	8
			Yellow Oxide	6	0	Yellow Oxide	21	0

## DEEP CHARCOAL

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	3	8	Black	11	12
			Magenta	0	4	Magenta	0	14
			Umber	1	16	Umber	5	8
			White	1	16	White	5	8

# UGL NUDECK WOOD AND CONCRETE RESTORATIVE COATING COLORS USING TWO TINT BASES – DO-IT-BEST GEOSHADES

## DEEP DESERT SAND

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	0	25	Black	2	23 ½
			Red Oxide	0	7	Red Oxide	0	24 ½
			Yellow Oxide	1	8 ½	Yellow Oxide	4	13 ¾

## FAWN

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	0	30	Black	3	9
			Red Oxide	0	15	Red Oxide	1	20 ½
			Yellow Oxide	3	15 ½	Yellow Oxide	12	6 ¾

## GEORGETOWN GRAY

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	1	31	Black	6	28 ½
			New Green	0	18 ½	New Green	2	¾
			Yellow Oxide	0	9	Yellow Oxide	0	31 ½

## HUNTER GREEN

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	1	16	Black	5	8
			Light Yellow	2	10	Light Yellow	8	3
			New Green	1	0	New Green	3	16
			White	0	9	White	0	31 ½

## MAHOGANY

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	2	20	Black	9	6
			Magenta	0	8	Magenta	0	28
			Red Oxide	0	24	Red Oxide	2	20
			White	0	4	White	0	14

# UGL NUDECK WOOD AND CONCRETE RESTORATIVE COATING COLORS USING TWO TINT BASES – DO-IT-BEST GEOSHADES

## MANOR BROWN

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	1	16	Black	5	8
			Red Oxide	0	8	Red Oxide	0	28
			Umber	8	0	Umber	28	0
			White	0	6	White	0	21

## NAVAJO WHITE

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Umber	0	23	Umber	2	16 ½
			Yellow Oxide	0	4	Yellow Oxide	0	14

## NEW PILGRIM RED

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	2	24	Black	9	20
			Magenta	2	23	Magenta	9	16 ½
			Red Oxide	2	28	Red Oxide	10	2

## PARCHMENT

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Umber	0	3 ½	Umber	0	12 ¼
			Yellow Oxide	0	15 ½	Yellow Oxide	1	22 ¼

## PILGRIM BLUE

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	1	9 ½	Black	4	17 ¼
			Blue	1	19 ½	Blue	5	20 ¼
			New Red	0	14	New Red	1	17

# UGL NUDECK WOOD AND CONCRETE RESTORATIVE COATING COLORS USING TWO TINT BASES – DO-IT-BEST GEOSHADES

## PLATINUM

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	0	6 ½	Black	0	22 ¾
			Magenta	0	3	Magenta	0	10 ½
			Yellow Oxide	0	15 ½	Yellow Oxide	1	22 ¼

## PRAIRE GOLD

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Light Yellow	0	24	Light Yellow	2	20
			Umber	0	16	Umber	1	24
			Yellow Oxide	1	11	Yellow Oxide	4	22 ½

## SABLE

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	1	16	Black	5	8
			Light Yellow	2	16	Light Yellow	8	24
			Red Oxide	2	4	Red Oxide	7	14
			White	0	16	White	1	24

## SAGE

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			New Green	0	12	New Green	1	10
			Umber	4	3	Umber	14	10 ½
			Yellow Oxide	0	11	Yellow Oxide	1	6 ½

## SALEM TAN

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Umber	1	7 ½	Umber	4	10 ¼
			Yellow Oxide	0	27 ½	Yellow Oxide	3	¼

# UGL NUDECK WOOD AND CONCRETE RESTORATIVE COATING COLORS USING TWO TINT BASES – DO-IT-BEST GEOSHADES

## SANDPIPER

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	0	12 ½	Black	1	11 ¾
			Red Oxide	0	1 ¼	Red Oxide	0	4 ¾
			Yellow Oxide	1	2	Yellow Oxide	3	23

## SIERRA REDWOOD

176 DARK BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Magenta	1	8	Magenta	4	12
			Red Oxide	3	12	Red Oxide	11	26
			Umber	6	0	Umber	21	0

## STONEHEDGE

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Black	0	20 ½	Black	2	7 ¾
			Blue	0	½	Blue	0	1 ¾
			Umber	0	20	Umber	2	6

## WINTER WHITE

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			Umber	0	2	Umber	0	7
			Yellow Oxide	0	2	Yellow Oxide	0	7

## WHITE

175 MEDIUM BASE

Quart Formula			Gallon Formula			3.5 Gallon Formula		
Colorant	OZS.	32nds	Colorant	OZS.	32nds	Colorant	OZS.	32nds
			White	0	10	White	1	3